ARTHUR M. SACKLER GALLERY & FREER GALLERY OF ART SMITHSONIAN INSTITUTION

LIGHT DURATION GUIDELINES FOR EXHIBITED WORKS OF ART

The following guidelines were written by members of the Department of Conservation and Scientific Research and the Curatorial Department to establish a procedure for determining the length of time that works of art may be safely exhibited. The Registrar keeps records of each object's exhibit history. Handscrolls and book records indicate what part or pages were exhibited.

CATEGORY	MATERIALS MATERIALS	EXPOSURE DURATION LIMIT	LIGHT LEVEL
A	 Extremely fugitive pigments & dyes Highly degraded paper & silk Albumen & tinted photographs Pre-19th century Japanese prints with color 	3 months over 5 years	5 footcandles (50 lux)
В	 Watercolors Paintings with organic pigments & dyes Textiles in poor condition or with organic dyes Colored papers Other Japanese woodblock prints 	6 months over 5 years	5 footcandles (50 lux)
C	 Paintings with mineral pigments Pastels Textiles in good condition or with aniline dyes Lacquer (depending on condition) Leather, dyed Photographs Carbon ink on paintings Pencil drawings Tempera paintings Most 20th century Japanese works on paper 	12 months over 5 years	5 –10 footcandles (50 – 100 lux)
D	 Ivory & bone Wood Lacquer (depending on condition) Oil paintings Leather, not dyed Enamels 	24 months over 5 years	5 –15 footcandles (50 – 150 lux)
E	 Stone Metals Glass Ceramics Jewels 	Unlimited	Unlimited